

Resistenstabel

A = Velegnet B = Eget D = Uegnet C = Bergrænset eget

Medie	Metaller					Kunststoffer				
	Stål	Støbejern	Aluminium	Bronze	Rustfrit 316	Nitril	Nylom	Viton	PTFE	EPDM
Acetaldehyde	C	C	B	D	A	D	B	C	A	C
Acetal opløsningsmiddel	B	B	A	A	A	D	D	D	A	D
Acetone	A	A	A	A	A	D	A	D	A	B
Acetylen	A	A	A	D	A	A	A	A	A	A
Acrylonitrile	A	C	B	A	A	D	D	D	A	A
Alkohol	B	C	B	B	B	A	A	A	A	A
Alkohol-amyl	B	C	B	B	A	A	A	A	A	A
Alkohol-butyl	B	C	B	B	A	A	A	A	A	A
Aluminium klorid (tør)	C	B	B	B	A	B	A	A	A	A
Aluminium sulfat (alun)	D	C	B	C	A	A	A	A	A	A
Alun	D	C	B	C	A	A	A	A	A	A
Amerikansk olie	B	B	A	A	A	A	A	A	A	A
Amin	A	C	A	A	A		A	D	A	
Ammoniak-bikarbonat	A	B	B	B	B	B	A	A	A	
Ammoniak-fosfat (divalent)	D	D	B	C	B	A	A	A	A	A
Ammoniak-fosfat (trivalent)	D	D	B	C	B	A	A	A	A	A
Ammoniak-hydroxid (28%)	A	C	C	D	B	B		A	A	A
Ammoniak-hydroxid (koncentreret)	A	C	C	D	B	B		A	A	A
Ammoniak-karbonat	C	B	B	B	B	B	A	B	A	
Ammoniak-klorid	D	D	C	D	C	B	A	A	A	
Ammoniak-monofosfat	D	D	B	D	B	A	B	A	A	A
Ammoniak-nitrat	D	D	B	D	A	A	A	A	A	A
Ammoniak-opløst	A	B	D	D	A	B			A	
Ammoniak-sulfat	D	C	B	B	B	A	A	A	A	A
Ammoniak-vandfri	A	B	B	D	A	B		C	A	
Amyl acetat	B	C	B	B	B	D	B	D	A	D
Ananas juice	D	C	A	C	A	A	A	A	A	A
Anilin	B	C	C	C	B	D	A	C	A	B
Anilin farvet	C	C	C	C	A	C	A	B	A	B
Animalsk olie	A	A	A	A	A	A			A	
Antimon triklorid	D	D	D	D	D	C	A	A	A	B
Arseniksyre	C	D	D	D	B	A	A	A	A	B
Asfalt Emulsion	B	B	C	A	A	B	A	A	A	D
Asfalt væske	B	B	C	A	A	C	A	A	A	D
Barium hydroxid	A	B	D	B	B	A	A	A	A	A
Bariumkarbonat	B	B	B	B	B	A	A	A	A	A
Bariumklorid	C	C	D	B	C	A	A	A	A	A
Bariumsulfat	B	C	D	C	B	A	A	A	A	A
Bariumsulfid	C	C	D	C	B	A	A	A	A	A
Benzin (blyholdig)	A	B	A	A	A	C	A	A	A	D
Benzin (blyfri)	A	B	A	A	A	D	A	B	A	D
Benzin (fly)	A	B	A	A	A	C	A	A	A	D
Benzin bitter	B	B	A	B	A	C	A	A	A	D
Benzaldehyd	C	B	A	A	A	D	A	D	A	C
Benzoesyre	D	D	B	B	B	A		A	A	D
Benzol	A	B	B	B	B	D	A	B	A	D
Blæk	B	D	C	C	A	A	A	A	A	
Blyukker	D	D	D	C	B	A	A	C	A	
Bomuldsfrøolie	B	C	B	B	B	A	A	A	A	A
Borax-syre	D	D	B	B	B	A	A	A	A	A
Borax-væske	C	C	C	A	B	A	A	A	A	A
Boremudder	A	B	B	B	A	A	A	A	A	A
Brine	C	C	B	B	B	A	A	A	A	A
Brint	B	B	A	B	A	A	A	A	A	A
Brintoverilte (fortyndet)	D	D	A	B	B	A		A	A	B
Brintoverilte (ufortyndet)	D	D	A	D	B	D			A	D
Brom tør	D	D	C	A	D	D		B	A	D
Brom våd	D	D	D	D	D	D		B	A	D
Brombrintsyre	D	D	D	D	D	C			A	
Buton	A	B	A	A	B	A	A	A	A	A
Butadiene	A	B	A	C	A	C	A	C	A	
Butylen	A	A	A	A	A	D			A	

Resistenstabel

A = Velegnet B = Eget D = Uegnet C = Bergrænset egnet

Medie	Metaller					Kunststoffer				
	Stål	Støbejern	Aluminium	Bronze	Rustfrit 316	Nitril	Nylom	Viton	PTFE	EPDM
Calcium bisulfid	D	D	C	B	B	A	A	A	A	A
Calcium carbonat	A	A	C	C	B	A	A	A	A	A
Calcium hydroxid	A	C	C	A	B	A	A	A	A	A
Calcium hypoklorit	D	D	C	D	C	B	A	A	A	A
Calcium sulfat	D	C	B	C	B	A	A	A	A	A
Citrus juice	D	D	C	B	B	A	A	A	A	A
Cyanbrinte	D	C	A	D	A		D		A	
Cyklohexane	A	A	A	A	A	C	A	A	A	
Damp 100% lavtryks	A	A	A	A	A	C		B	A	A
Diacetol alkohol	A	A	A	A	A	D			A	
Diesel Brændstof	A	A	A	A	A	A	A	A	A	D
Diethylamin	A	A	A	A	A	B			A	
Eddike	D	D	C	B	A	D		D	A	A
Eddike vandfri	D	D	B	C	B	C	D	D	A	C
Eddikesyre (kulsyreholdigt)	D	D	B	D	A	C	D	D	A	A
Eddikesyre (luftfri)	D	D	B	B	A	C	D	D	A	
Eddikesyre (rå)	D	C	B	C	A	D	D	D	A	
Eddikesyre (ren)	D	C	B	C	A	D	D	D	A	
Eddikesyre (10%)	D	C	B	C	A	D	D	D	A	A
Eddikesyre (80%)	D	C	B	C	A	D	D	D	A	C
Engelsk salt	C	C	A	B	B	A	A	A	A	A
Etan	A	B	A	A	B	A	A	A	A	A
Fatalsyre	D	C	B	B	B	C	A	C	A	
Fedt	A	A	A	B	A	A		A	A	D
Fedtsyre	C	D	B	B	A	B	A	A	A	D
Fenol	C	D	A	B	B	D	D	B	A	B
Fernis	B	C	A	A	A	C	A		A	
Ferré klorid	D	D	D	D	D	A	A	A	A	
Ferrinitrat	D	D	D	D	C	A	A	A	A	
Ferrisulfat	D	D	D	D	B	A	A	A	A	
Ferroklorid	D	D	D	B	D	A	A	A	A	
Ferro sulfat	D	D	D	B	B	A	A	A	A	
Fiskeolie	B	B	B	B	A	A	A	A	A	
Flour (tør)	D	D	D	D	D				A	
Fluorsiliciumbrinte	D	D	D	A	B				A	B
Flussyre	D	D	D	D	D		D		A	D
Formaldehyd (kold)	D	B	A	A	A	B	A		A	B
Formaldehyd (varm)	D	D	B	B	C	B	A		A	B
Fosforsyre (10% kold)	D	D	D	D	B	B	D	A	A	B
Fosforsyre (10% varm)	D	D	D	D	D	B	D	A	A	B
Fosforsyre (50% kold)	D	D	D	D	B	B	D	A	A	B
Fosforsyre (50% varm)	D	D	D	D	D	B	D	A	A	B
Fosforsyre (85% kold)	D	D	D	D	A	C	D		A	B
Fosforsyre (85% varm)	D	D	D	D	A	C	D		A	B
Freon (tør)	A	B	B	B	A	C		C	A	D
Frugtjuice	D	D	B	B	A	A	A	A	A	D
Fuel oil	A	B	A	B	A	A	A	A	A	
Furtural	D	B	A	A	A	D	A	D	A	
Gallussyre	D	D	A	C	B	A	A		A	
Garvesyre	C	C	C	B	B	A	A	A	A	
Gas (forbruger)	A	B	B	B	B	A	A	A	A	
Gas (natur)	A	B	B	B	A	A	A	A	A	
Gas LPG (flydende)	A	B	A	A	B			A	A	A
Gelatine	C	D	A	A	A			A	A	A
Glykose	B	B	A	A	A			A	A	A
Hexanol-tercicer	A	A	A	A	A				A	
Hydraulic olie	A	B	A	B	A	A	A	A	A	D
Isooktan	A	B	A	A	A	A	A	A	A	
Isopropylalkohol	A	B	B	B	B	C	A	A	A	A
Isopropylæter	A	B	A	A	A	C			A	
Jod	D	D	D	D	D	B	A	A	A	

Resistenstabel

A = Velegnet B = Eget D = Uegnet C = Bergrænset egnet

Medie	Metaller					Kunststoffer				
	Stål	Støbejern	Aluminium	Bronze	Rustfrit 316	Nitril	Nylom	Viton	PTFE	EPDM
Joddoform	C	C	C	C	A		A	A	A	
JP 4-5-6 Fuel	A	A	A	A	A	A	A	A	A	
Kaffe ekstrakt (varm)	D	C	A	B	A				A	
Kalium bisulfid	C	D	C	C	B	A	A	A	A	A
Kalium bromid (bromkalium)	C	D	C	C	A	A	A	A	A	A
Kalium cyanid	C	B	D	D	B	A	A	A	A	A
Kaliumdifosfat	A	A	B	B	A	A	A	A	A	A
Kaliumdikromat	B	C	A	D	B	A	A	A	A	A
Kaliumferricyanid	C	C	B	D	B	A	A	A	A	A
Kaliumferrocyanid	C	C	B	B	B	A	A	A	A	A
Kalium hydroxid (fortyndet kold)	A	A	D	D	A	A	C	B	A	A
Kalium hydroxid (til 70% kold)	A	A	D	D	A	B	D	D	A	A
Kalium hydroxid (il 70% varm)	A	B	D	D	B	B	D	D	A	A
Kaliumkarbonat	C	B	C	B	B	A	A	A	A	A
Kaliumklorat	D	B	C	B	B	A	A	A	A	A
Kaliumklorid	C	B	B	B	C	A	A	A	A	A
Kaliummineral	C	C	D	D	B	A	A	A	A	A
Kaliumnitrat	B	B	B	B	B	A	A	A	A	A
Kaliumpermanganat	B	B	B	B	B	A	A	A	A	A
Kaliumsulfat	B	C	A	B	B	A	A	A	A	A
Kaliumsulfid	C	B	B	B	A	A			A	A
Kaliumsulfid	C	B	B	B	A				A	A
Ketchup	D	D	D	D	A	A	A	A	A	
Keton	A	A	A	A	A	D	A	D	A	
Klor (våd)	D	D	D	D	D	D			A	C
Kloropløsningsmiddel (tør)	A	C	D	C	B	D	A	C	A	C
Klorbenzol (tør)	C	B	B	B	A	D	A	A	A	D
Kloroform (tør)	B	B	D	B	A	D	A	B	A	D
Klorsulfonsyre (tør)	B	B	B	B	B	D			A	
Klorsulfonsyre (våd)	D	D	D	D	D	D			A	
Kobberacetat	D	D	D	D	A				A	A
Kobberklorid	D	D	D	D	C	A	A	A	A	A
Kobbernitrat	D	D	D	D	B	A	A	A	A	A
Kobbersulfat	D	D	D	D	B	A	A	A	A	A
Kokos olie	C	C	B	B	B	A	A	A	A	
Koks gas	B	B	A	C	A	B		B	A	
Kornolie	B	C	B	B	B	A	A	A	A	
Kreosot olie	B	B	A	B	B	D	D	A	A	B
Kresylsyre	C	D	C	C	B	D	D	B	A	
Kromalun	D	B	C	C	A	B			A	
Kromsyre	D	D	D	D	C	D	D	C	A	B
Kulstof bisulfid	B	B	A	C	B	D	C	A	A	
Kultveilte (CO2)	A	B	A	A	A	B		A	A	A
Kulsyre (CO)	D	D	A	D	B	A	A	A	A	A
Kunstgødning (opløst)	C	C	B	C	B	B			A	
Kviksølv	A	A	C	D	A	A	A	A	A	
Magnesium bisulfat	C	B	B	B	A				A	
Magnesium hydroxid	B	B	D	B	A	A	A	A	A	A
Magnesium hydroxid (varm)	B	B	D	D	A	B	A	A	A	A
Magnesium klorid	C	D	D	B	B	A	A	A	A	A
Magnesium sulfat	C	B	B	B	B	A	A	A	A	A
Maleinsyre	D	D	B	B	B	A	A	A	A	
Mayonnaise	C	D	D	D	A	A	A	A	A	
Melasse rå	B	A	A	A	A	A	A	A	A	
Melasse spiselig	B	C	A	A	A	A	A	A	A	
Merkuri (Kviksølv)	A	A	C	D	A	A	A	A	A	
Merkuriklorid (klorkviksølv)	D	D	D	D	C				A	
Metan	A	B	A	A	B	A	A	A	A	A
Metylacetat	B	B	A	A	A	D		D	A	
Metylacetone	A	A	A	A	A	D		D	A	
Metylamín	A	B	A	D	A				A	

Resistenstabel

A = Velegnet B = Egnet D = Uegnet C = Bergrænset egnet

Medie	Metaller					Kunststoffer				
	Stål	Støbejern	Aluminium	Bronze	Rustfrit 316	Nitril	Nylom	Viton	PTFE	EPDM
Metylalkohol	A	B	B	B	B	A	A	B	A	A
Metylcellulose opløser	A	B	A	A	A				A	
Metylformat	C	C	C	A	B	D			A	
Metylklorid	B	B	D	A	A	C	A		A	C
Metylenklorid	B	B	A	A	A	D		C	A	C
Metylætyl	A	A	A	A	A	D	A	D	A	
Mineralvand	A	B	A	B	A	A	A	A	A	
Mineralsk olie	A	B	A	B	A	A	A	A	A	D
Minevand	C	D	D	C	C	A	A	A	A	
Monokloreddikesyre	D	D	C	C	D	D		C	A	
Myresyre (kold)	D	D	D	C	B	D	D		A	B
Myresyre (varm)	D	D	D	C	B	D	D		A	B
Mælkesyre (fortyndet kold)	D	D	D	A	A	B	D		A	B
Mælkesyre (fortyndet varm)	D	D	D	B	A	C	D		A	B
Mælkesyre (ufortyndet kold)	D	D	D	B	A	B	D		A	B
Mælkesyre (ufortyndet varm)	D	D	D	B	B	C	D		A	B
Nafta	A	B	A	B	B	A	A	A	A	
Naftalin	A	B	B	B	B	C	A	A	A	
Natriumacetat	B	C	B	B	B	B	A	C	A	A
Natrium aluminat	A	A	D	C	A	A	A	A	A	A
Natrium bikarbonat	C	C	B	B	B	A	A	A	A	A
Natrium bisulfat (10%)	C	D	D	B	A	A	A	A	A	A
Natrium borsurt salt	B	C	B	B	B	A	A	A	A	A
Natrium bromid (10%)	C	D	B	B	B	A	A	A	A	A
Natrium cyanid	C	B	D	D	B	A	A	A	A	A
Natrium fluorid	D	D	C	C	B	A	A	A	A	A
Natrium fosfat (trivalens)	B	C	D	C	B	B	A	A	A	A
Natrium hydroxid (kold) 20%	A	A	D	D	A	A	C	B	A	A
Natrium hydroxid (varm) 20%	A	A	D	D	A	B	D	C	A	A
Natrium hydroxid (kold) 50%	A	A	D	D	A	A	C	B	A	A
Natrium hydroxid (varm) 50%	A	A	D	D	A	B	D	D	A	A
Natrium hydroxid (kold) 70%	A	A	D	D	A	B	D	D	A	A
Natrium hydroxid (varm) 70%	A	B	D	D	B	B	D	D	A	A
Natrium hypoklorit	D	D	D	D	D				A	B
Natriumkarbonat	C	B	C	B	B	A	A	A	A	A
Natrium klorat	D	C	C	B	B	A	A	A	A	A
Natriumklorid	C	C	B	B	B	A	A	A	A	A
Natriumkromat	A	B	D	C	A	A	A	A	A	
Natrium sulfid	C	B	C	D	B	A	A	A	A	A
Natrium sulfid (varm)	C	C	D	D	B				A	A
Natrium thisulphate	D	B	B	B	A	A	A	A	A	A
Nikkelammoniumsulfat	D	D	D	D	A	A			A	
Nikkelklorid	D	D	D	D	B	A	A	A	A	A
Nikkelnitrat	D	D	C	D	B	A	A	A	A	A
Nikkelsulfat	D	D	D	D	B	A	A	A	A	A
Nikotinsyre	C	B	A	A	A				A	
Nitrobenzol	B	B	C	D	B	D		C	A	
Nitrogen	A	A	A	A	A	A	A	A	A	
Olie raffineret (råolie)	A	B	A	B	A	A	A	A	A	
Olie bitter (råolie)	C	C	A	C	A	A		A	A	
Olie-vand emulsion	A	B	A	A	A	A	A	A	A	
Oliesyre	C	C	B	B	B	A	A	A	A	
Olivenolie	C	B	A	B	A	A	A	A	A	
Olium	B	C	B	B	B	D	D	D	A	
Opløsningsmidler	A	A	A	A	A	D			A	
Oxalsyre	D	D	C	B	B	C	C	A	A	B
Oxygen	A	B	A	A	A				A	A
Ozon (våd)	C	C	B	B	A				A	A
Ozon (tør)	B	A	A	A	A				A	A
Palmeolie	B	C	A	B	B	B	A	A	A	
Palmitinsyre	C	C	B	B	B	B	A	A	A	C

Resistenstabel

A = Velegnet B = Eget D = Uegnet C = Bergrænset egnet

Medie	Metaller					Kunststoffer				
	Stål	Støbejern	Aluminium	Bronze	Rustfrit 316	Nitril	Nylom	Viton	PTFE	EPDM
Paraffin	A	B	A	A	A	A	A	A	A	
Paraformaldehyd	D	B	B	B	B	B	A		A	B
Pentan	A	B	A	A	A	A	A	A	A	D
Perkloretylen (tør)	B	B	A	C	A	D		A	A	D
Pikrinsyre	D	D	C	B	B	C			A	A
Porcelæns-træolie	A	A	A	C	A	A	A	A	A	
Propangas	A	B	A	A	B	A	A	A	A	B
Propylalcohol	A	B	A	A	A	A	A	A	A	
Porpylen glycol	A	B	A	B	B	A	C	A	A	
Pyrogallussyre	C	B	B	B	B	A	A	A	A	
Rensevæske (tør)	B	B	A	C	A	D	A	B	A	
RP - 1 fuel	A	A	A	A	A	A	A	A	A	
Råolie (mild)	B	B	A	B	A	A		A	A	
Råolie (syrlig)	C	C	A	C	A	A		A	A	
Salatolie	D	C	B	B	B	A	A	A	A	
Salicylsyre	D	D	C	C	A	A	A	A	A	
Salpeterholdig gas	D	C	B	D	A				A	
Salpetersyre (10%)	D	D	D	D	A	C	D	A	A	A
Salpetersyre (30%)	D	D	D	D	A	C	D	A	A	B
Salpetersyre (80%)	D	D	B	D	A	D	D	B	A	C
Salpetersyre (100%)	D	D	B	D	A	D	D	B	A	D
Salpetersyrling (10%)	D	D	D	D	B	C		A	A	
Salt	C	C	B	B	B	A	A	A	A	
Saltsyre	D	D	D	D	D	B	D		A	A
Sennep	D	B	B	A	A	A	A	A	A	
Shellak (afbleget)	B	B	A	A	A	A			A	
Sukkerroe saft	B	B	A	A	A	A	A	A	A	
Sulfatvæske sort	D	C	B	C	B	C	A	C	A	
Sulfatvæske grøn	D	C	B	C	B	C	A	C	A	
Sulfatvæske hvid	D	C	B	C	B	C	A	C	A	
Svinefedt	B	C	A	A	B	A	A	A	A	
Svovl	B	C	A	D	B	D			A	D
Svovlbrinte (våd)	D	D	C	D	B	C	A	A	A	B
Svovlbrinte (tør)	C	B	B	C	A	C	A	A	A	B
Svovldioxid (tør)	C	B	A	B	A	C	A	A	A	B
Svovlholdig syre	D	D	C	C	B	C	C	A	A	A
Svovlsyre (0-7%)	D	D	B	C	B	B	C	A	A	A
Svovlsyre (20%)	D	D	D	C	D	C	C	A	A	A
Svovlsyre (50%)	D	D	D	B	D	C	D	A	A	A
Svovlsyre (100%)	B	B	D	A	A	D	D	B	A	D
Svovltrioxid (tør)	B	B	A	B	A	C	A		A	B
Syntetisk gas	B	B	B	B	B	A	A	A	A	
Sæbeopløsning	B	B	C	A	A	A		A	A	A
Sølvnitrat	D	D	D	D	B	C	A	A	A	A
Søvand	C	D	C	C	A	A	A	A	A	
Talg olie	A	B	B	B	B	A	A	A	A	
Terpentin olie	B	B	A	B	A	A	A	A	A	
Tetraklorkulstof (tør)	B	B	B	C	A	D	A	B	A	
Tetraklorkulstof (våd)	D	D	C	D	B	D	A	B	A	
Tetraæter	A	C	B	B	B		A		A	
Tinklorid	D	D	D	C	D	A	A	A	A	
Tjære og tjæreolie	B	A	A	A	A	B		A	A	
Tomatjuice	D	C		C	A	A	A	A	A	
Transformerolie	A	B	A	B	A	A	A	A	A	
Tributyl fosfat	B	A	A	A	A	C			A	
Trikloretylen	B	C		B	B	D	A	B	A	D
Træolie	A	A	A	B	A	A	A	A	A	
Tuluol	A	A	A	A	A	D	A	B	A	D
Tørrende olie	A	B	C	C	D	A	A		A	
Urinstof	B	C	B	B	B		A		A	B
Vand destilleret	C	D	A	A	A	A	A	A	A	A

Resistenstabel

A = Velegnet B = Egnat D = Uegnet C = Bergrænset egnat

Medie	Metaller					Kunststoffer				
	Stål	Støbejern	Aluminium	Bronze	Rustfrit 316	Nitril	Nylom	Viton	PTFE	EPDM
Vand frisk	B	C	A	A	A	A	A	A	A	A
Vaselin	A	C	B	B	B	A	A	A	A	A
Vegetabilsk olie (spiselig)	D	B	A	B	A	A	A	A	A	
Vegetabilsk olie (uspiselig)	B	B	A	B	A	A	A	A	A	
Vin	D	D	D	A	A	A	A	A	A	
Vinsyre	D	D	B	A	B	C	A	A	A	B
Voks	B	B	A	A	A	A	A	A	A	
Whisky	D	D	D	A	A	A	A	A	A	
Xylol (tør)	A	B	A	A	A	D	A	A	A	D
Zinkhydrosulfid	B	B	D	C	A	A	A	A	A	
Zinkklorid	D	C	D	D	D	B	A	A	A	
Zinksulfat	D	D	D	B	B	A	A	A	A	
Æblejuice	D	D	B	C	B	A	A	A	A	
Æblesyre	D	D	B	B	B	A	A	A	A	
Æter	A	B	A	B	A	C	C	D	B	
Ætylalkohol	A	B	B	B	B	A	A	A	A	A
Ætylacetat	B	C	B	C	B	D	A	D	A	C